



RAPID PREP

GARNET ABRASIVE

Garnet abrasive is often used as an alternative to silica sand as it produces less dust and is safer than its hazardous counterpart, silica sand. When used properly abrasive blasting with Garnet provides comparable production rates as silica sand.

FEATURES

- Suitable for wet or dry abrasive blasting
- Increases productivity
- Recyclable up to 5 times
- Non-Toxic
- Does not draw moisture

AVAILABLE SIZES

- **MEDIUM** 30/60
- **MEDIUM FINE** 80



ABRASIVE CONSUMPTION (lbs. per hour) PER BLAST NOZZLE

NOZZLE SIZE	NOZZLE PRESSURE					
	70 psi	80 psi	90 psi	100 psi	120 psi	140 psi
No. 2 1/8"	105	115	130	140	165	190
No. 3 3/16"	230	260	290	320	375	430
No. 4 1/4"	420	460	500	560	660	760
No. 5 5/16"	650	725	825	900	1050	1200
No. 6 3/8"	945	1050	1150	1260	1475	1700
No. 7 7/16"	1300	1450	1600	1750	2050	2350
No. 8 1/2"	1660	1850	2000	2250	2650	3000
No. 10 5/8"	2660	2900	3125	3520	4100	4750
No. 12 3/4"	3750	4180	4500	5060	5950	6800